



MULTIPURPOSE EPOXY 2-PART HIGH STRENGTH ADHESIVE

DESCRIPTION:

AfteK Multipurpose Epoxy Adhesive is a 2-part, non sag, high strength adhesive. It is intended for bonding of a variety of common building materials to vertical and horizontal surfaces. Common applications include fireplace surrounds, stairs, feature stone walls, tiles, rockeries and indoor garden displays.

RECOMMENDED USES:

- Bonding of Masonry, precast concrete, stone panels marble, granite, slate, ceramic tiles on walls or overhead in interior or exterior applications
- Feature walls
- Fireplace surrounds & Facades
- Insitu formed concrete
- Precast concrete
- Grouting/fixing anchor bolts
- Bonding to metals
- Concrete structures
- Outdoor entertaining areas
- Fabrication of head stones and other decorative stone items
- Statues and fountains
- Pipe and crack repair

FEATURES AND BENEFITS:

- Permanent bond 5 – 6 hours
- Cure time 12 hrs at 25°C
- Non staining on all stone types
- Non sag up to 30 mm thick
- Mix ratio 1:1
- Solvent free
- Permanent bond – no performance decrease over time
- High performance properties
- High tensile and compressive strength
- Excellent chemical resistance

APPLICATION

SUBSTRATE PREPARATION:

Clean the surface and remove any dust, unsound material, plaster, oil, paint, grease, corrosion deposits or algae. Roughen the surface and remove any laitance and expose aggregate by light scabbling or grit-blasting. For painted surfaces: remove all paint or coatings using paint stripper or mechanically abrade surface.

MIXING

The mix ratio is 1:1 by volume, 1 parts Part A and 1 part Part B. Care should be taken to ensure that Aftek Multipurpose Epoxy is thoroughly mixed. The entire contents of the hardener (Part B) tin should be poured into the base (Part A) tin and the two materials thoroughly mixed using a suitable slow-speed drill and high shear mixing paddle.

Mix for 2 minutes until a fully uniform grey colour is obtained; the sides of the tins should be scraped, mixing should continue for a further 2 minutes. **DO NOT OVER MIX AS THIS MAY INCORPORATE AIR BUBBLES.**

To facilitate mixing and application at temperatures below 10°C, the separate components should be warmed in hot water bath or conditions to room temp up to a maximum temperature of 25°C before beginning to mix. If heated to 25°C, the subsequently mixed material will have a pot life that will be reduced to 45 minutes. Alternatively, the material should be stored in an environment controlled to 20°C and only removed immediately before use.

ONLY MIX MATERIAL THAT CAN BE USED WITHIN THE SETTING TIME.

Working time up to 45min @ 25°C.



Aftek

MULTIPURPOSE EPOXY

Application-

Aftek Multipurpose Epoxy should be applied as soon as the mixing process has been completed

PROPERTIES

TYPICAL PROPERTIES	
Mixed consistency	Thixotropic paste with no sag or slump
Appearance	Part A: White Part B: Black Grey when mixed
Specific Gravity	1.45/Lt
Solid Content	100%
Chemical Resistance	Excellent (see chart)
Heat Distortion Temp	90°C
Pot Life	50-60 min @ 25°C
Compressive Strength	100MPa
Flexural Strength	22MPa approx..
Modulus of Elasticity	Approx. 11x10 ³ MPa
Hardness	>80 shore D
Service Temp	-20°C to +70°C
Cure time @ 25°C	12hours
Full cure @ 25°C	3 days
Min application temperature	7°C
Working time	Approx 45min @ 25°C
Bond Strength	>15MPa

*Tested to ASTM D570

CHEMICAL RESISTANCE*

Chemical	Resistance
Citric Acid 100%	Excellent
Acetic Acid 5%	Excellent
Sodium Hydroxide 30%	Excellent
Diesel fuel/petrol	Excellent
Sugar Solutions	Very good
Tartaric Acid 100%	Very good
Hydrocarbons	Very good
Phosphoric Acid	Very good

*Resistant to spillage. Surface staining may result from exposure to some aggressive chemicals. All spills should be quickly removed and washed. Over exposure may result in surface degradation.

IMPORTANT NOTES

Aftek Multipurpose Epoxy when mixed in large volumes, greater than 10 litres is highly likely to cure faster reducing the pot life of the mixed material in the tin. **Low temperature working:** the minimum application temperature is 5°C. In temperatures below 10°C, the separate components should be heated in warm water (up to 25°C) or stored in a temperature controlled environment for 12 hours before use.

High temperature working: at ambient temperatures above 30°C, the material should be stored in the shade or in an air-conditioned environment for 12 hours before use

DO NOT dilute Aftek Multipurpose Epoxy with solvents as this will severely affect the ultimate performance of the product. Only mix as much Aftek Multipurpose Epoxy that can be used within the Pot Life (45-60 minutes @ 25°C). Surfaces must be rigid. Not suitable for blueboard, cement sheeting or any other compressed material – may cause substrate to internally delaminate under stress. Not recommended for sandstone and other fissile stones – these stones can be porous or veneered which will cause the bond to fail by delamination of the stone surface. Consult Aftek Technical department for additional information.

PACKAGING:

Item 14509:

1 Lt Kit :

Part A 1x 0.5 Lt (White)

Pt B 1x 0.5 Lt (Black)

Item 14506:

2 Lt Kit :

Part A 1x 1.0 Lt (White)

Part B 1x 1.0 Lt (Black)

Item 14504:

4 Lt Kit :

Part A 1x 2 Lt (White)

Part B 1 x 2 Lt (Black)

Item 14505:

20 Lt Kit:

Part A 1x 10 Lt (White)

Part B 1x 10 litre Part B (Black)

MULTIPURPOSE EPOXY

CLEAN UP:

Clean up should be done as soon as possible after mixing using warm water with soap or detergent.

COVERAGE

Average coverage : 20 litres covers 20m² @1mm thick when applied as per the table below.

SHELF LIFE

Product will remain usable for a period of 2 years if stored between 5°C and 35°C in an unopened container.

SAFETY & FIRST AID:

Avoid contact with skin and eyes and avoid breathing the vapors. Store under cover, out of direct sunlight and in a well ventilated area. Keep away from all sources of ignition – no smoking.

If poisoning occurs contact a doctor or Poisons Information Centre. If swallowed, DO NOT induce vomiting. Give a glass of water. If in eyes, hold eyes open, flood with water for at least 15 minutes and see a doctor. Refer to Material Safety Data Sheet for further information.

BONDING OF TILES

Apply mixed Aftek Multipurpose Epoxy in dabs at each corner and centre of panel (minimum) to be bonded – dabs must be equivalent to 20% coverage tile area

Minimum dab sizes per tile to achieve 10% coverage with 5 dabs @ 20mm thick	
Tile Size	Dab Diameter
300 x 300mm	35mm
600 x 600mm	70mm
900 x 900mm	70mm

Minimum dab sizes per tile to achieve 10% coverage with 3 dabs	
Stack Stone Size	Dabs & Diameter
400 x 100mm	3 dabs min @ 100mm in size

Product: Aftek Multipurpose Epoxy adhesive
 Issue Date: NOV 2017
 Issue No: DO2



The information and any recommendations relating to the application and end-use of all IAFTEK products are provided in good faith based on AFTEK's knowledge and experience of the products. In applications, the differences in materials, and variances of substrates and actual site conditions can vary such that no warranty in respect of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be taken as inferred either from this information, or from any written recommendations, or from any other advice offered by AFTEK. The proprietary rights of third parties must be observed. All orders are accepted subject to our sale terms and conditions. All users should always refer to the most recent and up to date issue of the Technical Data Sheet for the product concerned, which is available on request. It is recommended that products should always be properly stored, handled and applied under tested and recommended conditions. PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.